

SECTION 93

LIQUID ASPHALTS

Liquid asphalts shall conform to Section 93 of the Caltrans Standard Specifications and these City Standard Specifications.

93-1.03 Mixing and Applying. - Liquid asphalt shall not be heated during manufacture, storage, or construction to a degree to cause the formation of carbonized particles, and in no case shall the temperature be higher than 10 degrees fahrenheit below the actual flash point.

Unless otherwise authorized by the Engineer, no liquid asphalt, except tack coats, shall be applied when the air temperature is lower than 50 degrees fahrenheit.